



CLASSIC CRETETM SBR 100

Liquid Polymer Bonding agent for cement containing mixes

Product:

Classic Crete SBR 100 is a one component styrene butadiene rubber latex bonding agent. Classic Crete SBR 100 is designed to improve the physical properties of cement mixes and slurries.

Applications

Classic Crete SBR 100 is ideally designed for use in the following applications.

- Bonding of new to old concrete when used as a slurry coat.
- To produce various traditional cement/sand adhesive mortars such as block mortar, plaster/render and tile adhesive.
- To produce a mechanical key prior to rendering of various plaster mixes on concrete, brick and block surfaces.

Advantages:

- Successfully increases the bonding/adhesion of cement mixes.
- Effective plasticizer giving improved workability and cohesion.
- Improved mechanical and physical properties by increasing tensile, flexural and adhesive strengths.
- Good freeze/thaw resistance
- Chloride free.
- Non-toxic can be used for concrete in contact with potable water.

Standards:

Classic Crete SBR 100 complies with:

- ASTM C1059-99, Type 1, when tested in accordance with test method ASTM C 1042.
- ASTM C 932, for compressive strength.
- ASTM C 1438, for compressive strength

METHOD OF USE

SUBSTRATE PREPARATION

The substrate should be sound, clean and free from contamination. Surface laitance should be removed by acid etching. Exposed steel reinforcements should be grit blasted or wired brushed to a bright finish to insure it is clean of all surface contaminations.

Technical Properties @ 25 °C:

Colour: White
Specific gravity: Around 1.0
Slant shear strength
ASTM C1042-99 ≥ 5.0 MPa
Type I (dry)

Tensile bond strength: ≥ 1200 KPa
ASTM C932 (wet condition)

For patch repair, out back the edges of the repair areas to a minimum of 10 mm depth to avoid thin repair thicknesses. Presoak substrates with water prior to commencing the repair.

Mixing

In general Classic Crete SBR 100 should be added and mixed with the clean water prior to dry materials for better dispersion.

1) As bonding agent slurry:

The recommended mix to produce slurry consistency can be achieved by mixing 1 **Classic Crete SBR 100** : 2 OPC cement by volume

2) As a bonding and waterproofing additive for site mixed cement/sand adhesive mortar:

The following table shows the mix design proposed to improve the adhesion of traditional cement/sand mortars such as block mortar, plaster/render and tile adhesive.

Component	Qty by Volume
Cement	3
Sand	6
Water*	1-3
Classic Crete SBR 100	1

*Based on type of sand and humidity.

Application

1) As a bonding agent slurry

Use a stiff brush to apply a thick coat to presoaked surfaces. Application of the subsequent render, mortar or screed should take place while the bond coat is still wet (tacky). DO NOT apply on dry bond coats. (if bond coat dries before subsequent application, roughen the dry coat before subsequent application, roughen the dry coat before applying a further coat of **Classic Crete SBR 100** slurry.)

CLASSIC CRETE™ SBR 100

Liquid Polymer Bonding agent for cement containing mixes

2) As a bonding and waterproofing additive for site mixed cement/sand adhesive mortar.

Apply workable site mixed cement/sand adhesive mortar prepared with Classic Crete SBR 100 based on best practices method of application for purpose required.

Cleaning:

All tools should be cleaned immediately after use with fresh clean water. Hardened materials should be cleared mechanically.

Packaging:

Classic Crete SBR 100 is available in 5,10,20 and 50 kg containers.

Storage:

Classic Crete SBR 100 has a shelf life of 12 months from date of manufacture if stored at temperature between 5 °C and 35 °C in closed packaging.



Cautions

Health and Safety

Classic Crete SBR 100 is nontoxic. Avoid skin and eye contact. Gloves and eye protection should be worn. The use of barrier cream is recommended on exposed areas of the skin.

In case of accidental contact with eyes, immediately flush with plenty of water for at least 10 minutes and seek medical advice.

TAMILNADU

Corporate Office

PRIMADONN BUILDTECH PVT LTD

No. 349, First Floor, Srinivasa Nagar, Kavaripttai, Gummidipoondy 601 206.

Ph+91-8220513172,

Admin Office:

No.605, Selva Vinayaga Nagar, Grant Lyon Village, Ponneri Tk., Thiruvalluvar Dt., Ph+91-6379174327, +91-8438276059.

Manufacturing Unit

No.603, Selva Vinayaga Nagar, Grant Lyon, Vadagarai, Chennai 600 052. Ph.+91-9444907177

KARNATAKA

Corporate Office:

PRIMADONN CONSTRUCTION CHEMICALS (P) LTD.,

Talacauvery Layout, Basavanagar, Bangalore 560 037. Ph.+9150878429, +91-9345411355.

PONDICHERRY

Branch Office

192/A, Chinna Subburaya Pillai Street, Near Vaikal Cutting, Puducherry 605 001. Ph.0413-4208833, 91-+9514709240

Distributors

151, Chinna Subburaya Pillai Street, Near Vaikal Cutting, Puducherry 605 001. Ph.0413-2222100, 91-+9345561820

Email: Info@Primadonn.com, www.Primadonn.com

